



Performance Results

	GVP-C400	GVP-S350	GVP-S200
Solar Transmittance	80	50	53
Solar Absorptance	14	44	40
Solar Reflectance	6	6	7
Visible Light Transmission	90	31	33
Visible Light Absorptance	2	64	62
Visible Light Reflectance (Exterior)	8	5	5
Visible Light Reflectance (Interior)	8	6	6
Emmissivity	0.91	0.86	0.87
U-Value (Summer)	1.08	0.96	0.97
U-Value (Winter)	1.14	1.03	1.04
Shading Coefficient	0.97	0.74	0.75
Solar Heat Gain Coefficient	0.83	0.65	0.66
UV Transmittance (300-350 Nanos)%	<2	<2	<2
Total Solar Energy Rejected	17	36	35

Notes: This test data contains results arrived at only after employing specific test procedures and standards. The included data does not constitute a recommendation for, endorsement of, or certification of the product or material tested. This data is provided for informational purposes only. ShatterGARD Safety & Security Window Films, Inc. makes no representation or warranty, expressed or implied, including the implied warranties of merchantability or fitness for a particular purpose, that its products will conform to these test data. Extrapolation of data from the sample or samples relating to the batch or lot from which data were obtained may not correlate and should be interpreted accordingly with caution. ShatterGARD shall not be responsible for variations in quality, composition, appearance, performance, or other feature of similar subject matter produced by persons or under conditions over which ShatterGARD has no control. Performance results were generated from testing 1/8" (3mm) thick clear glass and are subject to variations within industry standards.





Physical and Thermal Properties

	GVP-C400	GVP-S350	GVP-S200
Tensile Strength ASTM D 882 (PSI)	30,000	30,000	30,000
Elongation At Break ASTM D 882 (%)	160	160	160
Yield Stress (5%) ASTM D 882 (PSI)	15,750	15,750	15,750
Break Strength (lbs./in.)	122	122	122
Yield Strength (5%) (lbs./in.)	64	64	64
Tear Strength ASTM D 1004 Graves Tear Test (Initial)	6.8	6.8	6.8
Tensile Modulus ASTM D 882 (PSI)	558,000	558,000	558,000
Puncture Strength ASTM D 4830 (lbs.)	71	71	71
Peel Strength (grams/inch of width)	3,300	3,300	3,300
Poisson's Ratio ASTM D 882	0.40	0.40	0.40
Abrasion Resistance (%) ASTM D 1003-92 ASTM D 1044 100 Cycles	<5	<5	<5
ANZI Z 97.1	Pass	Pass	Pass
CPSC CFR 1201, Category II	Fail	Fail	Fail
GSA Security Criteria Performance Condition Daylight Application (4 PSI / 28 PSI/msec)	3b	3b	3b
BS 6206, Class C	Pass	Pass	Pass
Flame Spread Index ASTM D 882	2	2	2
Smoke Index ASTM D 882	31	31	31
Flash Temperature (°F) ASTM D 1929	735	735	735
Combustion Rate	NEGLIGIBLE	NEGLIGIBLE	NEGLIGIBLE
Melting Point (°C)	263	263	263
Self Ignition (°F) ASTM D 1929	755	755	755

Notes: This test data contains results arrived at only after employing specific test procedures and standards. The included data does not constitute a recommendation for, endorsement of, or certification of the product or material tested. This data is provided for informational purposes only. ShatterGARD Safety & Security Window Films, Inc. makes no representation or warranty, expressed or implied, including the implied warranties of merchantability or fitness for a particular purpose, that its products will conform to these test data. Extrapolation of data from the sample or samples relating to the batch or lot from which data were obtained may not correlate and should be interpreted accordingly with caution. ShatterGARD shall not be responsible for variations in quality, composition, appearance, performance, or other feature of similar subject matter produced by persons or under conditions over which ShatterGARD has no control. Performance results were generated from testing 1/8" (3mm) thick clear glass and are subject to variations within industry standards.

